


Aluminium Alloy Checkered Plate (5 Bar Pattern) (AA 3105/AA 5052/AA 5754)



Chemical Composition

AA3105

%	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
Min.				0.30	0.20				
Max.	0.6	0.7	0.30	0.80	0.80	0.20	0.40	0.10	Remainder

AA 5052

%	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
Min.					2.2	0.15			
Max.	0.25	0.40	0.10	0.10	2.8	0.35	0.10		Remainder

AA 5754

%	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
Min.					2.6				
Max.	0.40	0.40	0.10	0.50	3.6	0.30	0.20	0.15	Remainder

Thickness (T)	Width (W)	Length (L)
1.5 mm	4 ft	8 ft
2 mm	4 ft	8 ft
3 mm	4 ft	8 ft/12 ft
4 mm	4 ft	8 ft
4.5 mm	4 ft	8 ft/12 ft
5 mm	4 ft	8 ft
5.4 mm	4 ft	8 ft/12 ft
6 mm	4 ft	8 ft/12 ft

Thickness (T)	Width (W)	Length (L)
3 mm	5 ft	10 ft
4.5 mm	5 ft	10 ft
5.4 mm	5 ft	10 ft
6 mm	5 ft	10 ft
3 mm	64 "	124 "
3 mm	64 "	157 "
3 mm	6.5 ft	19 ft
8 mm	4 ft	8 ft
10 mm	4 ft	8 ft
12 mm	4 ft	8 ft