


Aluminium Perforated Sheet (AA 1100/AA 5052)



Chemical Composition

AA 1100

%	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
Min.	Si + Fe		0.05						
Max.	0.95		0.20	0.05			0.10		Remainder

AA 5052

%	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
Min.					2.2	0.15			
Max.	0.25	0.40	0.10	0.10	2.8	0.35	0.10		Remainder

Thickness (T)	Width (W)	Length (L)	Outer Dia. (OD)	Pitch (P)
0.5 mm	4 ft	8 ft	3 mm	5 mm
0.6 mm	4 ft	8 ft	3 mm	5 mm
0.7 mm	4 ft	8 ft	3 mm	5 mm
0.8 mm	4 ft	8 ft	3 mm	5 mm
1 mm	4 ft	8 ft	3 mm	5 mm
1 mm	4 ft	8 ft	5 mm	8 mm
1.2 mm	4 ft	8 ft	2.5 mm	5 mm
1.2 mm	4 ft	8 ft	3 mm	5 mm
1.2 mm	4 ft	8 ft	5 mm	8 mm
1.5 mm	4 ft	8 ft	3 mm	5 mm
1.5 mm	4 ft	8 ft	5 mm	8 mm
2 mm	4 ft	8 ft	3 mm	5 mm
2 mm	4 ft	8 ft	5 mm	8 mm
3 mm	4 ft	8 ft	3 mm	5 mm